AF/GAU2813



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant:

Gurtej Singh Sandhu et al.

Title:

METHOD TO REDUCE FIXED CHARGE IN CVD OZONE DEPOSITED FILMS

Docket No.:

303.573US1

Filed: Examiner:

April 22, 1996 Matthew Wipple Serial No.: 08/636,069

Due Date: January 26, 1999

Group Art Unit: 2813

Box AF

Assistant Commissioner for Patents

Washington, D.C. 20231

RECEIVED

We are transmitting herewith the following attached items (as indicated with an "X"):

JAN 28 1999

X A return postcard.

X An Amendment and Response Under 37 C.F.R.§ 1.116 (8 Pages).

GROUP 2100

Please consider this a PETITION FOR EXTENSION OF TIME for sufficient number of months to enter these papers and please charge any additional required fees or credit overpayment to Deposit Account No. 19-0743.

SCHWEGMAN, LUNDBERG, WOESSNER & KLUTH, P.A. P.O. Box 2938, Minneapolis, MN 55402 (612-373-6900)

Atty: Thomas W. Leffert

Reg. No. 40,697

(GENERAL)

PEDITED PROCEDURE - EXAMINING GROUP 2813

1-30-99 Robert AFMAU

S/N 08/63/6408

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant:

Gurtej Singh Sandhu et al.

Examiner: Matthew Wipple

Serial No.:

08/636,069

Group Art Unit: 2813

Filed:

April 22, 1996

Docket: 303.573US1

Title:

METHOD TO REDUCE FIXED CHARGE IN CVD OZONE DEPOSITED

FILMS

AMENDMENT & RESPONSE UNDER 37 C.F.R. § 1.116

Box AF Assistant Commissioner for Patents Washington, D.C. 20231

In response to the final Office Action mailed October 26, 1998, please amend the application as follows to place the claims in better condition for appeal:

IN THE SPECIFICATION

On page 6, line 6, after "reaction" please remove "volume of gas, above the"

IN THE CLAIMS

Please cancel claims 25-29 without prejudice.

RECEIVED

JAN 2 8 1999

GROUP 2100

- 1. (Twice amended) A chemical vapor deposition (CVD) process for depositing SiO₂ films on a substrate surface, said process comprising [the steps of]:
 - [(a)] disposing the substrate within a chemical vapor deposition reaction chamber;
 - [(b)] introducing a gas volume of SiO₂ precursors into said chamber;
 - [(c)] admitting a gas volume of ozone into the chamber;
 - [(d)] illuminating, with a source of high intensity light, the volume of gas located within [a chemically reactive distance of the substrate assembly surface,]the reaction chamber without [illuminating]directing the high intensity light at the substrate assembly.